


CHEMTREAT AH7



PRODUCT DESCRIPTION

CHEMTREAT AH 7 is an inhibited acid descalant for the removal of hardness deposits and iron oxides. This product may be used at temperatures up to 50°C (120°C) in plant that is manufactured in steel, aluminum, copper or stainless steel.

	Units	BCI Specifications	Test Methods
Appearance	-	white/off-white powder	ASTM-E2680
PH as supplied	-	1.0	ASTM-D1293

TREATMENT AND DOSAGE REQUIREMENTS

For removing hardness deposits, a sample of scale should, if possible be removed from the plant and placed in a solution of the solvent at the temperature at which the clean will be carried out.

The solution concentration required is in the range of 50 – 100 kg/m³ of water depending on the quantity and characteristics of the scale being removed. The contact time also depends on a number of factors including the quantity and characteristics of the scale, the strength of the cleaning solution and the ability to recirculate this solution. However the recommended contact time is up to 6 hours.

PRODUCT BENEFITS

- Effective removal of hardness deposits.
- May be used to dissolve iron oxide deposits.
- Contains an inhibitor which minimizes attack on parent metal.
- May be stored where liquid descalants are not permitted.

DISCLAIMER

Any sale by BCI, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed. Otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED. Each customer must determine the suitability of seller concerning a possible use of any product, service or design is intended, or should be construed to grant any license under any patent or other intellectual property right.

الصناعات الكيماوية الأساسية
BASIC CHEMICAL INDUSTRIES



HEAD OFFICE

P.O Box 1053, Dammam 31431, Saudi Arabia
T: +966 13 821 7777 F: +966 13 847 26 48
Email: Sales@bci.com.sa

الفرع الرئيسي

ص.ب ١٠٥٣، الدمام ٣١٤٣١، المملكة العربية السعودية
ت: +٩٦٦ ١٣ ٨٢١ ٧٧٧٧ ف: +٩٦٦ ١٣ ٨٤٧ ٢٦٤٨
البريد الإلكتروني: Sales@bci.com.sa